Optical Fiber Diameter Analyser (OFDA100)
Micron Test Report

Kraussdale Alpacas
5169 Kraussdale Rd, East Greenville
PA 18041, US


Date: 20-Aug-26
Shear ID: 285722
Test No: 628157

Animal and Sample Description

Animal Name:	Kraussdale Feliz	Date of Birth (Age):	13-Aug-25
Registry #:	36301027	Sample Location:	GRID
Breed:	Huacaya	Sample Date:	25-Apr-26
Sex:	Male	Previous Shear Date:	13-Aug-25
Colour:	500 - True Black	Total Fleece Wt (lbs):	1.9

Laboratory Data

Mean Fiber Diameter:	16.6 microns	Mean Staple Length:	105 mm
Standard Deviation:	3.5 microns	Length Standard Deviation:	0.4 mm
Coefficient of Variation:	21.1 %	Length Coefficient of Variation:	0.4 %
Spin Fineness:	16.2 microns	Mean Curvature:	55.3 deg/mm
Fibers Greater Than 30 microns:	0.7 %	SD Curvature:	40.0 deg/mm
Comfort Factor:	99.3 %		



The OFDA100 base cut method minimizes the effects of environmental variability and provides more accurate comparisons of genetic capability. Average staple length is determined from multiple staples measured using a calibrated electronic length instrument, and is important for managing yarn processing outcomes.

Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

SGS General Terms and Conditions
The validity of this document may be confirmed by contacting the address shown below
SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com