Optical Fiber Diameter Analyser (OFDA100)
Micron Test Report

Ariya Alpacas
411 Brill Road, West Bolton
Quebec J0E 2T0 CA


Date: 13-Apr-21
Shear ID:
Test No: 600348

Animal and Sample Description

Animal Name:	Calypso Ii'S Cria (2020) Eh	Date of Birth (Age):	5-Jun-20
Registry #:		Sample Location:	Right Side
Breed:		Sample Date:	1-Mar-21
Sex:	Male	Previous Shear Date:	
Colour:	Light Fawn	Total Fleece Wt (lbs):	

Laboratory Data

Mean Fiber Diameter:	15.5 microns	Comfort Factor:	99.6 %
Standard Deviation:	3.1 microns	Mean Curvature:	50.7 deg/mm
Coefficient of Variation:	19.9 %	SD Curvature:	20.6 deg/mm
Spin Fineness:	14.9 microns	Medullated Fibers:	2.0 %
Fibers Greater Than 30 microns:	0.4 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

SGS General Terms and Conditions
The validity of this document may be confirmed by contacting the address shown below
SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com