# Optical Fiber Diameter Analyser (OFDA100)
# Micron Test Report

Forest Cove Farm & Country Market
32129 Hwy 17, Chalk River
ON K0J 1J0, CA


Date: 22-Jul-26
Shear ID: 283307
Test No: 627580

## Animal and Sample Description

| | | | |
|---|---|---|---|
| Animal Name: | Forest Cove Amias' NEMO | Date of Birth (Age): | 9-Aug-25 |
| Registry #: | 36248117 | Sample Location: | GRID |
| Breed: | Huacaya | Sample Date: | 2-May-26 |
| Sex: | Male | Previous Shear Date: | 3-May-25 |
| Colour: | 204 - Medium Fawn | Total Fleece Wt (lbs): | |

## Laboratory Data

| | | | |
|---|---|---|---|
| Mean Fiber Diameter: | 18.9 microns | Mean Staple Length: | 123 mm |
| Standard Deviation: | 4.5 microns | Length Standard Deviation: | 2.1 mm |
| Coefficient of Variation: | 23.6 % | Length Coefficient of Variation: | 1.7 % |
| Spin Fineness: | 18.8 microns | Mean Curvature: | 56.9 deg/mm |
| Fibers Greater Than 30 microns: | 2.2 % | SD Curvature: | 42.4 deg/mm |
| Comfort Factor: | 97.8 % | | |




The OFDA100 base cut method minimizes the effects of environmental variability and provides more accurate comparisons of genetic capability. Average staple length is determined from multiple staples measured using a calibrated electronic length instrument, and is important for managing yarn processing outcomes.

## Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
**Business Manager**

Ioasa Kosena
**Authorised Signatory**

SGS General Terms and Conditions
The validity of this document may be confirmed by contacting the address shown below
SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com