



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Sugar Pike Alpacas
401 Addle Lane, Canton
GA 30115, US

Date: 18-Aug-25
Shear ID: 276820
Test No: 624071

Animal and Sample Description


Animal Name: AUTUMNSUN's Taz
Registry #: 36122387
Breed: Huacaya
Sex: Male
Colour: 209 - Light Brown

Date of Birth (Age): 18-Jul-24
Sample Location: GRID
Sample Date: 13-Apr-25
Previous Shear Date: 18-Jul-24
Total Fleece Wt (lbs): 4.21

Laboratory Data

Mean Fiber Diameter: 17.3 microns
Standard Deviation: 4.0 microns
Coefficient of Variation: 23.1 %
Spin Fineness: 17.1 microns
Fibers Greater Than 30 microns: 0.5 %
Comfort Factor: 99.5 %

Mean Staple Length: 128 mm
Length Standard Deviation: 5.8 mm
Length Coefficient of Variation: 4.5 %
Mean Curvature: 46.2 deg/mm
SD Curvature: 35.9 deg/mm



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com