



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Sugar Pike Alpacas
401 Addle Lane, Canton
GA 30115, US

Date: 18-Aug-25
Shear ID: 276799
Test No: 624050

Animal and Sample Description


Animal Name: AUTUMNSUN's KORAY
Registry #: 36187812
Breed: Huacaya
Sex: Female
Colour: 410 - Dark Brown

Date of Birth (Age): 8-Sep-21
Sample Location: GRID
Sample Date: 13-Apr-25
Previous Shear Date: 27-May-25
Total Fleece Wt (lbs): 5.87

Laboratory Data

Mean Fiber Diameter: 25.9 microns
Standard Deviation: 5.2 microns
Coefficient of Variation: 20.1 %
Spin Fineness: 25.0 microns
Fibers Greater Than 30 microns: 16.4 %
Comfort Factor: 83.6 %

Mean Staple Length: 65 mm
Length Standard Deviation: 1.8 mm
Length Coefficient of Variation: 2.8 %
Mean Curvature: 50.8 deg/mm
SD Curvature: 35.7 deg/mm



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com