



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Rhonda Deschner
PO Box 919, Wimberley
TX 78676, US

Date: 10-Jun-22
Shear ID: 234645
Test No: 607536

Animal and Sample Description


Animal Name: TP 2021-Vision
Registry #: 35456896
Breed: Huacaya
Sex: Male
Colour: 201 - Beige

Date of Birth (Age): 1-Mar-21
Sample Location: GRID
Sample Date: 2-May-22
Previous Shear Date: 15-Jun-21
Total Fleece Wt (lbs): 6.3

Laboratory Data

Mean Fiber Diameter: 19.9 microns
Standard Deviation: 4.7 microns
Coefficient of Variation: 23.3 %
Spin Fineness: 19.8 microns
Fibers Greater Than 30 microns: 2.4 %
Comfort Factor: 97.6 %

Mean Staple Length: 113 mm
Length Standard Deviation: 1.7 mm
Length Coefficient of Variation: 1.5 %
Mean Curvature: 43.9 deg/mm
SD Curvature: 18.0 deg/mm
Medullated Fibers: 4.3 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com