Optical Fiber Diameter Analyser (OFDA100)
Micron Test Report

Tierra Prometida Alpacas
4805 Farm to Market 32, Fischer
TX 78623, US


Date: 9-Jul-25
Shear ID: 276122
Test No: 623456

Animal and Sample Description

Animal Name:	SNOWMASS ARTEMISIA	Date of Birth (Age):	1-Sep-22
Registry #:	36220694	Sample Location:	GRID
Breed:	Huacaya	Sample Date:	27-Apr-25
Sex:	Female	Previous Shear Date:	20-Apr-24
Colour:	100 - White	Total Fleece Wt (lbs):	

Laboratory Data

Mean Fiber Diameter:	17.8 microns	Mean Staple Length:	112 mm
Standard Deviation:	3.7 microns	Length Standard Deviation:	3.0 mm
Coefficient of Variation:	21.0 %	Length Coefficient of Variation:	2.7 %
Spin Fineness:	17.3 microns	Mean Curvature:	56.0 deg/mm
Fibers Greater Than 30 microns:	0.5 %	SD Curvature:	36.2 deg/mm
Comfort Factor:	99.5 %	Medullated Fibers:	0.8 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

SGS General Terms and Conditions
The validity of this document may be confirmed by contacting the address shown below
SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com