



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Wild Rose Suri Ranch
3623 Harmony Church Rd, Havre de Grace
MD 21078-1015, US

Date: 7-Sep-21
Shear ID: 227951
Test No: 604470

Animal and Sample Description


Animal Name: Knolveston's Beta Max
Registry #: 36016815
Breed: Suri
Sex: Male
Colour: 204 - Medium Fawn

Date of Birth (Age): 8-Jun-19
Sample Location: GRID
Sample Date: 17-Apr-21
Previous Shear Date: 18-Apr-20
Total Fleece Wt (lbs):

Laboratory Data

Mean Fiber Diameter: 19.9 microns
Standard Deviation: 5.2 microns
Coefficient of Variation: 26.0 %
Spin Fineness: 20.3 microns
Fibers Greater Than 30 microns: 4.1 %
Comfort Factor: 95.9 %

Mean Staple Length: 137 mm
Length Standard Deviation: 20.7 mm
Length Coefficient of Variation: 15.1 %
Mean Curvature: 31.8 deg/mm
SD Curvature: 18.0 deg/mm



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com