



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Red Granites Ranch
1021 Red Granite Ranch Rd, Livermore
CO 80536, US

Date: 25-Sep-24
Shear ID: 264179
Test No: 621175

Animal and Sample Description


Animal Name: RED GRANITES FERN
Registry #: 35123415
Breed: Huacaya
Sex: Female
Colour: 209 - Light Brown

Date of Birth (Age): 26-Jul-16
Sample Location: GRID
Sample Date: 31-May-24
Previous Shear Date: 3-Jun-23
Total Fleece Wt (lbs): 6.125

Laboratory Data

Mean Fiber Diameter: 19.1 microns
Standard Deviation: 4.5 microns
Coefficient of Variation: 23.7 %
Spin Fineness: 19.0 microns
Fibers Greater Than 30 microns: 1.5 %
Comfort Factor: 98.5 %

Mean Staple Length: 61 mm
Length Standard Deviation: 4.4 mm
Length Coefficient of Variation: 7.2 %
Mean Curvature: 64.3 deg/mm
SD Curvature: 43.5 deg/mm



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com