



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Red Granite Ranch
1021 Red Granite Ranch Rd, Livermore
CO 80536, US

Date: 25-Aug-26
Shear ID: 285366
Test No: 628565

Animal and Sample Description


Animal Name: RED GRANITES SKY WALKER BY ALYD
Registry #: 36291601
Breed: Huacaya
Sex: Male
Colour: 360 - Bay Black

Date of Birth (Age): 9-Jun-25
Sample Location: GRID
Sample Date: 5-Jun-26
Previous Shear Date: 9-Jun-25
Total Fleece Wt (lbs): 3.2

Laboratory Data

Mean Fiber Diameter: 15.2 microns
Standard Deviation: 4.3 microns
Coefficient of Variation: 27.9 %
Spin Fineness: 15.8 microns
Fibers Greater Than 30 microns: 0.7 %
Comfort Factor: 99.3 %

Mean Staple Length: 74 mm
Length Standard Deviation: 4.3 mm
Length Coefficient of Variation: 5.7 %
Mean Curvature: 56.7 deg/mm
SD Curvature: 41.3 deg/mm



The OFDA100 base cut method minimizes the effects of environmental variability and provides more accurate comparisons of genetic capability. Average staple length is determined from multiple staples measured using a calibrated electronic length instrument, and is important for managing yarn processing outcomes.

Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com