



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Red Granite Ranch
1021 Red Granite Ranch Rd, Livermore
CO 80536, US

Date: 24-Aug-26
Shear ID: 285279
Test No: 628478

Animal and Sample Description


Animal Name: RED GRANITES COVE BAY
Registry #: 36407316
Breed: Huacaya
Sex: Female
Colour: 410 - Dark Brown

Date of Birth (Age): 28-Jul-25
Sample Location: GRID
Sample Date: 5-Jun-26
Previous Shear Date: 28-Jul-25
Total Fleece Wt (lbs): 3.5

Laboratory Data

Mean Fiber Diameter: 18.9 microns
Standard Deviation: 4.0 microns
Coefficient of Variation: 21.3 %
Spin Fineness: 18.4 microns
Fibers Greater Than 30 microns: 1.3 %
Comfort Factor: 98.7 %

Mean Staple Length: 89 mm
Length Standard Deviation: 4.1 mm
Length Coefficient of Variation: 4.6 %
Mean Curvature: 47.4 deg/mm
SD Curvature: 36.9 deg/mm



The OFDA100 base cut method minimizes the effects of environmental variability and provides more accurate comparisons of genetic capability. Average staple length is determined from multiple staples measured using a calibrated electronic length instrument, and is important for managing yarn processing outcomes.

Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com