



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Whistling Pines Ranch
499 4 1/2 Avenue, Clayton
WI 54004, US

Date: 16-Jul-24
Shear ID: 264707
Test No: 619163

Animal and Sample Description


Animal Name: WHISTLING PINES JERICO by VONTAE
Registry #: 36256020
Breed: Suri
Sex: Male
Colour: 204 - Medium Fawn

Date of Birth (Age): 7-Jul-23
Sample Location: GRID
Sample Date: 31-May-24
Previous Shear Date: 7-Jul-23
Total Fleece Wt (lbs): 8.5

Laboratory Data

Mean Fiber Diameter: 19.1 microns
Standard Deviation: 4.4 microns
Coefficient of Variation: 22.9 %
Spin Fineness: 18.9 microns
Fibers Greater Than 30 microns: 1.8 %
Comfort Factor: 98.2 %

Mean Staple Length: 208 mm
Length Standard Deviation: 5.3 mm
Length Coefficient of Variation: 2.5 %
Mean Curvature: 28.4 deg/mm
SD Curvature: 31.9 deg/mm



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com