



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Memory M-Acres

Date: 25-Sep-20
Shear ID: 204386
Test No: 500634

Animal and Sample Description


Animal Name: MACRES MAVERICK BY PICASSO
Registry #: 35558095
Breed: Suri
Sex: Male
Colour: 410 - Dark Brown

Date of Birth (Age): 8-Jul-19
Sample Location: GRID
Sample Date: 27-Apr-20
Previous Shear Date:
Total Fleece Wt (lbs): 4.00

Laboratory Data

Mean Fiber Diameter: 19.9 microns
Standard Deviation: 4.3 microns
Coefficient of Variation: 21.8 %
Spin Fineness: 19.5 microns
Fibers Greater Than 30 microns: 1.6 %
Comfort Factor: 98.4 %

Mean Staple Length: 141 mm
Length Standard Deviation: 5.5 mm
Length Coefficient of Variation: 3.9 %
Mean Curvature: 11.2 deg/mm
SD Curvature: 14.2 deg/mm
Medullated Fibers: %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Jude Davidson
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool@sgs.com Web: www.wooltesting.sgs.com