Optical Fiber Diameter Analyser (OFDA100)
Micron Test Report

Memory M-Acres


Date:	25-Sep-20
Shear ID:	204372
Test No:	500649

Animal and Sample Description

Animal Name:	WI SPECIAL EDITION	Date of Birth (Age):	12-Jan-15
Registry #:	35326281	Sample Location:	GRID
Breed:	Suri	Sample Date:	27-Apr-20
Sex:	Female	Previous Shear Date:	13-May-19
Colour:	201 - Beige	Total Fleece Wt (lbs):	6.50

Laboratory Data

Mean Fiber Diameter:	23.6 microns	Mean Staple Length:	88 mm
Standard Deviation:	5.0 microns	Length Standard Deviation:	21.3 mm
Coefficient of Variation:	21.0 %	Length Coefficient of Variation:	24.1 %
Spin Fineness:	23.0 microns	Mean Curvature:	7.7 deg/mm
Fibers Greater Than 30 microns:	8.6 %	SD Curvature:	9.8 deg/mm
Comfort Factor:	91.4 %	Medullated Fibers:	%



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Jude Davidson
Authorised Signatory

SGS General Terms and Conditions

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: nz.wool.timaru@sgs.com Web: www.wooltesting.sgs.com