Optical Fiber Diameter Analyser (OFDA100)
Micron Test Report

Spross Hollow Alpacas
7218 Exeter Ave, Spring Branch
AL, 78070, US


Date: 27-May-21
Shear ID:
Test No: 601579

Animal and Sample Description

Animal Name:	Dembe Steel	Date of Birth (Age):	28-Sep-19
Registry #:	35376743	Sample Location:	GRID
Breed:	Huacaya	Sample Date:	3-Apr-21
Sex:	Male	Previous Shear Date:	
Colour:	402 - Medium Silver Grey	Total Fleece Wt (lbs):	

Laboratory Data

Mean Fiber Diameter:	20.2 microns	Mean Staple Length:	93 mm
Standard Deviation:	5.1 microns	Length Standard Deviation:	2.5 mm
Coefficient of Variation:	25.2 %	Length Coefficient of Variation:	2.7 %
Spin Fineness:	20.4 microns	Mean Curvature:	48.6 deg/mm
Fibers Greater Than 30 microns:	3.5 %	SD Curvature:	19.7 deg/mm
Comfort Factor:	96.5 %		



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

SGS General Terms and Conditions
The validity of this document may be confirmed by contacting the address shown below
SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com